



Water resistance

Following investigations into the resistance of the lacquers used to protect our floors we can confirm that our materials are water resistant. This does not apply to oiled floors, as the surface protection on an oiled floor is designed to be periodically replaced as part of a regular maintenance regime. As this is beyond the control of our production we are unable to confirm oiled floors as being water resistant.

Our lacquer finishes are supplied by Klumpp who are producers of floor finishes. The Wood Coating test report confirms stain tests with the following liquids with the result for coffee being the most relevant in respect of water resistance:

- Vinegar-16 hours
- Sodium Hydroxide / Caustic Soda (NaOH) – 10 minutes
- Coffee- 16 hours
- Iodine- 1 hour

The result achieved for all liquids was rated as 5 (no visible change)